

310 A BASIC



LLDPE cast stretch film for wrapping machines without prestretch group where no special needs are required.

| Characteristic | Method | Unit | Direction | 23 μm | Tolerances |
|---------------------------|--------------|------|------------------------------|-------|------------|
| Impact resistance | ASTM D1709 A | g | - | 80 | 10% |
| Tensile strength at break | ASTM D882 B | MPa | Machine Direction | 27 | 10% |
| | | | Transversal Direction | 20 | 10% |
| Tensile strength at yield | ASTM D882 B | MPa | Machine Direction | 6 | 10% |
| | | | Transversal Direction | 5 | 10% |
| Elongation at break | ASTM D882 B | % | Machine Direction | 450 | 10% |
| | | | Transversal Direction | 550 | 10% |
| Tear Resistance | ASTM D1922 | mN | Machine Direction | 1731 | 10% |
| | | | Transversal Direction | 2708 | 10% |
| Stretch | Hipac | % | - | 125 | 5% |
| Cling | Hipac | g | - | 130 | 10% |
| | | | | | |

| Coloured | Slippery | AUV 6/12 months | Antistatic | Net Roll | Cling Out/In/Both | Low Temperature | Printed | Double Edges |
|---|----------|-----------------|------------|----------|-------------------|-----------------|---------|--------------|
| × | × | × | × | × | × | × | × | × |
| | | | | | | | | |
| HIPAC STRETCH FILM HAS BE DESIGNED TO BE 100% RECY | | | | | | | | |

The above values are to be considered as indicative in order to facilitate the choice and usage, but are not given for guarantee purposes. Hipac Group reserves the right to modify them, if necessary, without previous notice. Products in conformity with our Technical Specification. The present document is property of Hipac S.p.A. It cannot be copied, published or redistributed without prior written consent of Hipac S.p.A.