

333 A RIGID POWER



LLDPE cast stretch film suitable for applications on “entry level” wrapping machines with medium prestretch (up to 250%). Thickness downgauging maintaining the same performance allows 333 to replace any kind of power film saving up to 35% material

Characteristic	Method	Unit	Direction	15 µm	Tolerances
Impact resistance	ASTM D1709 A	g	-	105	10%
Tensile strength at break	ASTM D882 B	MPa	Machine Direction	33	10%
			Transversal Direction	18	10%
Tensile strength at yield	ASTM D882 B	MPa	Machine Direction	14	10%
			Transversal Direction	7.6	10%
Elongation at break	ASTM D882 B	%	Machine Direction	370	10%
			Transversal Direction	620	10%
Tear Resistance	ASTM D1922	mN	Machine Direction	2154	10%
			Transversal Direction	5645	10%
Prestretch*	Hipac	%	-	240	5%
Cling	Hipac	g	-	130	10%

* Intended as the sum of prestretch and post-stretch (lay on tension).
 In case of coloured stretch film these values should be reduced by 10%.
 In case of additives these values should be reduced by 5%.
 In case of printed film these values should be reduced by 5%.

Coloured	Slippery	AUV 6/12 months	Antistatic	Net Roll	Cling Out/In/Both	Low Temperature	Printed	Double Edges
								

HIPAC STRETCH FILM HAS BEEN
DESIGNED TO BE 100% RECYCLABLE



The above values are to be considered as indicative in order to facilitate the choice and usage, but are not given for guarantee purposes. Hipac Group reserves the right to modify them, if necessary, without previous notice. Products in conformity with our Technical Specification. The present document is property of Hipac S.p.A. It cannot be copied, published or redistributed without prior written consent of Hipac S.p.A.