

# 999 A/M EXTRA RIGID




LLDPE cast prestretched film, suitable for wrapping machines without prestretch group and for hand wrap.

Characteristic	Method	Unit	Direction	7 $\mu$ m	Tolerances
Impact resistance	ASTM D1709 A	g	-	39	10%
Tensile strength at break	ASTM D882 B	MPa	Machine Direction	75	10%
			Transversal Direction	20	10%
Tensile strength at yield	ASTM D882 B	MPa	Machine Direction	38	10%
			Transversal Direction	5	10%
Elongation at break	ASTM D882 B	%	Machine Direction	130	10%
			Transversal Direction	750	10%
Tear Resistance	ASTM D1922	mN	Machine Direction	1010	10%
			Transversal Direction	2410	10%
Stretch	Hipac	%	-	10	5%
Cling	Hipac	g	-	125	10%

Coloured	Slippery	AUV 6/12 months	Antistatic	Net Roll	Cling Out/In/Both	Low Temperature	Printed	Double Edges
✘	✘	✘	✘	✔	✘	✔	✘	✔

All 999 extra rigid is produced by default with double edges.



The above values are to be considered as indicative in order to facilitate the choice and usage, but are not given for guarantee purposes. Hipac Group reserves the right to modify them, if necessary, without previous notice. Products in conformity with our Technical Specification. The present document is property of Hipac S.p.A. It cannot be copied, published or redistributed without prior written consent of Hipac S.p.A.